

Data sheet – PVC Foam board (Palight®)

Property	Test Method	Units - SI	Value
Physical			
Relative density*	In-house	g/cm ³	0.65 - 0.70
Water absorption	ASTM D-570	%	0.5 - 0.8
Mechanical			
Tensile strength at yield	ASTM D-638	MPa	16
Elongation at break	ASTM D-638	%	30
Flexural strength at yield	ASTM D-790	MPa	28
Flexural modulus*	ASTM D-790	MPa	900
Charpy impact strength	ASTM D-256	J/m	29
Shore D hardness		value	N/A
Thermal			
Service temperature*	In-house	°C	-10 to 55
Heat distortion temperature*	In-house	°C	63
Vicat softening temperature	ASTM D-648	°C	75
Coefficient of thermal expansion*	ASTM D-1525	cm/cm°C	6.70
Electrical			
Dielectric strength	ASTM D-257	Ω	5x10 ¹
Surface resistivity	ASTM D-257	Ω-cm	2x10 ¹
Flammability			
EN13501			B, s1,d0
BS 476 Part 7			Class 1
UL 94			V-0
NSP 92501,5			M-1, M-2
DIN 4102			B-2

Notes:

Foamed PVC has a self-extinguishing property. If ignited in air, it will die by itself. Subsequently, foamed PVC complies with the most demanding fire resistance standards as indicated by these representative results.

The above tables cannot be directly compared due to the different test methods utilised, unless where indicated *. Relative density is stated for 3mm standard products.

Simply Plastics Ltd

Unit 6 Fanton Hall | Doublegate Lane | Wickford | Essex | SS12 9JF

www.simplyplastics.com | info@simplyplastics.com | 01268 570703